



Art.-No.: 6.0520.1000

**0520**

## PE-Thinner

### Characteristics

Mixture of organic solvents for the dilution of polyester systems (4CR 2500 spray filler, polyester Putty).

### Tech Tip

4CR 0520 PE thinner contains no reactive components.

Therefore, do not add more than 5% to polyester materials.

In order to accelerate the drying, it is advisable to take a short pause between flashing so that the solvents can escape.

### Application

The amount that has to be added depends on the processing guidelines of the main product.

Make sure that the products are very well mixed with 4CR 0520 PE thinner.

- Keep container tightly closed.
- Not near open flames, heat, Process or store ignition sources.

Also because the material can become electrostatically charged, ground properly when removed.

### Technical Data

Density at 20°C:	0.9 g/cm <sup>3</sup> (DIN 53217)
Viscosity at 20°C:	12 s (DIN 53211/4)
Flash point	4°C (DIN 53213)
Ignition temperature	460°C (DIN 51794)

### Storage and Transportation

Can be stored for at least 3 years in the closed original container.

