



Art.-No.: 6.2030.1000

2030

Contour Putty for Plastics

Characteristics

4CR 2030 is an elastic contour putty especially developed for the use on coatable plastic parts. Excellent adhesivity, high elasticity, fast drying and easy to sand.

Application

The substrate has to be clean, dry and free of grease. Abrade the surface. Remove all traces of old coats, which are not in good condition and firmly adhering.

Do not apply on thermoplastic or acid containing ground coats.

Mix well 4CR 2030 with hardener 2900.
Apply within appropriate temperature range (not less than +10°C object temperature).



Technical Data

Mixing ratio	100 : 2
Hardener	2900 BPO
Pot life (20°C)	4 - 5 Min.
Sandable	after approx. 20 - 30 min. (object temp. 20°C)
Colour	dark-grey (approx. RAL 7024)

Storage and Transportation

At least 1 year, if stored in tightly closed original containers.