



Art.-No.: 6.2310.2000
6.2310.0010

2310

V-Multi Putty

Characteristics

4CR 2310 is a high build body filler for both filling and finishing.

Adhesion to steel sheets, galvanized sheets, aluminium, tin plated substrates and glass fibre reinforced plastics.

- Short drying time
- easy sanding
- pore free application by high thickness coatings are further characteristics of this high quality product.

Overcoat with 4CR Filler.

V.O.C. Value

EU limiting value for the product (cat. B/b): 250 g/l (2007)
This product contains max. 6 g/l VOC [0.050 lbs/gal]

Application

The substrate must be clean, dry and free of grease.
Sand first the surface! Remove old layers of paint or primer, which are not adhesive or completely dry.

Do not apply on thermoplastic or acid-containing products.

Mix well with Hardener.

Drying:

Metal temp. 20°C: Sandable after approx. 20 min.

Technical Data

Colour shade	beige
Mixing ratio	100 : 2
Hardener	BPO 2900 / 2910
Pot life	3 - 4 min.

Storage and Transportation

At least 12 months, if stored in tightly closed original containers.

