



Art.-No.: 6.2350.0800
 6.2350.1600
 6.2350.1400
 6.2350.2632
 6.2350.9000

2350

Multi Soft Putty

Characteristics

4CR 2350 is a high quality 2-component polyester universal putty for smoothing irregularities in the car refinishing sector, vehicles and mechanical engineering.

Professional quality with excellent adhesion on: iron, steel, galvanized metal, aluminium, glass fibre and carbon fibre reinforced compounds.

Highly filling by fine grain composition, maximum stability on vertical surfaces, no cracking on the edges by fine sanding, will give a compact, smooth surface of top quality.

very easy to sand even with P240.



V.O.C. Value

EU limiting value for the product (cat. B/b): 250 g/l (2007)
 This product contains max. 4 g/l VOC [0.03 lbs/gal]

Tech Tip

Once 4CR 2350 has dried, it can be recoated using all customary paint systems. if needed seal the filled areas with 4CR 2K-Filler.

For example 4CR 4270 or 4280 Premium HS Filler.

Application

The substrate must be clean, dry and free of grease. Sand the surface. Remove old thermoplastic coats (NC- or 1K-acrylic paints), synthetic resins as well as acid-containing products (eg. Washprimer).

Technical Data

Hardener	BPO 2900, 2910
Mixing ratio	2 weight %
Pot life	3 - 4 Min.
Drying (Object Temp. 20°C)	Sandable after approx. 25 min.
Colour	Light grey

Storage and Transportation

At least 1 year, if stored in tightly closed original containers.