



Art.-No.: 6.2355.1600

**2355**

## Multi Soft Putty Trillanium

### Characteristics

4CR 2355 is a high quality 2-component polyester universal putty for smoothing irregularities in the car refinishing sector, vehicles and mechanical engineering.

Professional quality with excellent adhesion on: iron, steel, galvanized metal, aluminium, glass fibre and carbon fibre reinforced compounds.

Highly filling by fine grain composition, maximum stability on vertical surfaces, no cracking on the edges by fine sanding, will give a compact, smooth surface of top quality.

very easy to sand even with P240

because of it's colour you also have a sanding guide.



### V.O.C. Value

EU limiting value for the product (cat. B/b): 250 g/l (2007)

This product contains max. 4 g/l VOC [ 0.03 lbs/gal]

### Tech Tip

Once 4CR 2355 has dried, it can be recoated using all customary paint systems. Seal the filled areas with 4CR 2K-Filler.

### Application

The substrate must be clean, dry and free of grease. Sand the surface. Remove old thermoplastic coats (NC- or 1K-acrylic paints), synthetic resins as well as acid-containing products (eg. Washprimer).

### Technical Data

Hardener	BPO 2900
Mixing ratio	2 weight %
Pot life	3 - 4 Min.
Drying (Object Temp. 20°C)	Sandable after approx. 25 min.
Colour	blue

### Storage and Transportation

At least 1 year, if stored in tightly closed original containers.