



Art.-No.: 6.2360.1600

**2360**

## Multi Soft Putty green

### Characteristics

4CR 2360 is a multifunctional 2K polyester putty for levelling dents, scratches and bumps in the car repair as well as the automotive and machine manufacturing.  
 Very good adhesion on iron, steel, aluminum, GRP and galvanized substrates.  
 Highly stable on vertical surfaces.

### V.O.C. Value

EU limiting value for the product (cat. B/b): 250 g/l (2007)  
 This product contains max. 4 g/l VOC [ 0.03 lbs/gal]

### Tech Tip

In the case of deep bumps and dents, level the damaged area by bulging.

In the case of deep bumps and dents, apply the putty in several layers.

Adhesion to iron, steel, aluminum, zinc, GRP

### Application

Application conditions above +10°C and up to 90% humidity. Polyester putty will not harden at less than +10°C.

The substrate must be clean, dry and free of grease. Sand the surface. Remove old thermoplastic coats (NC- or 1K-acrylic paints), synthetic resins as well as acid-containing products (eg. Washprimer).

Mix very well putty and hardener. Once 4CR 2360 has dried, it can be recoated with all standard paint systems. Isolate putty spots with 4CR 2K Sanding Filler.

### Technical Data

|                |  |
|----------------|--|
| Colour         | green  |
| Mixing ratio   | 2 weight %   |
| Hardener       | BPO 2900   |
| Pot life       | 3 - 4 Min.   |
| Drying         | Sandable after approx. 25 min. (Object Temp. 20°C) |
| Heat resistant | up to 80°C   |

### Storage and Transportation

At least 1 year, if stored in tightly closed original containers.

