



Art.-No.: 6.2620.0900

2620

Nitrocellulose Putty

Characteristics

CR 2620 is an one component fine putty on nitrocellulose base of good adhesion to iron, steel and hard, sanded old coatings.

V.O.C. Value

EC limiting value for the product (cat. B/e): 840 g/l (2007)
This product contains max. 444 g/l VOC [3,7 lbs/gal]

Application

Curing time:
Consider a flash off time of approx. 1 h before the application of the next coat.

Drying:
Object Temp. 20°C: recoatable and sandable after 1 - 2 h.

Degrease, derust and sand the substrate. Remove completely the old thermoplastic paintings. Then apply 2620 without any hardener. Avoid coat thickness more than 80 µm per coat and allow a cure time of approx. 1 h between the next coats. After drying 2620 may be sanded without any difficulty. Re-coatable with all of the usual paint systems.



Technical Data

Colour	grey-green
Coat thickness / dry film	max. 80 µm dry film per coat

Storage and Transportation

At least 1 year, if stored in tightly closed original containers.