



Art.-No.: 6.2625.0250

2625

NC-Combi stopper

Characteristics

4CR 2625 is an one component fine putty on nitrocellulose base with good adhesion to iron, steel and hard, sanded old coatings.

V.O.C. Value

EC limiting value for the product (cat. B/e): 840 g/l (2007)
This product contains max. 444 g/l VOC [3,7 lbs/gal]

Application

Drying
Recoatable and sandable after 1 - 2 h (20°C object temperature).

Degrease, derust and sand the substrate. Remove completly the old thermoplastic paintings. Then apply the NC-Combi stopper without any hardener. Avoid coat thickness more than 80 µm per coat and allow a cure time of approx. 1 h between the next coats. After drying 4CR 2625 may be sanded without any difficulty. Re-coatable with all usual paint systems.



Technical Data

Colour	grey
Content	250 g
Coat thickness	max. 80 $\hat{1}$ / ₄ m per coat
Flash off time	approx. 1 h per coat

Storage and Transportation

At least 1 year, if stored in tightly closed original containers.