



Art.-No.: 6.5210.1000

5210

UBC Bitumen brushable

Characteristics

4CR 5210 is a thixotrope, brushable anti gravel and anti corrosion coating with sound deadening properties based on bitumen.

After drying remains waterproof elastic coating that protects against various climates and gravel.

Tech Tip

5210 is applied as an anti gravel and anti corrosion protection for instance for chassis, wheel-housings and side-skirts of cars, trucks and coaches. The product is also applied as sound deadening coating in carriage- and container constructions.

Applicable in:

- Coach work industry
- Garages, workshops
- Body repair shops
- Ship building

Application

The surfaces to be treated must be clean, dry, rust-, dust- and grease free.

5210 can be applied without dripping in very thick layers by brush or spatula.

Depending on the application the product can be thinned with a solvent.

If thicker layers are wanted it is to be recommended to dry the layers in between.

Technical Data

Completely dried (at ± 20°C, 65% RH)	10 - 12 h (± 500 m²/m)
Dry to touch (at ± 20°C, 65% RH)	90 - 120 Minutes (± 500 m²/m)
Solid content	75,6 - 77,6 %
Density (20°C) DIN 51757	1,26 - 1,30 kg/ltr
Viscosity (20°C) Brookfield	1040 - 2000 mPas (Spindle 6 / V½)
Consistence	Pasty, brushable, good sag-resistance
Basic raw materials	Bitumen, fillers and solvents
Colour	black
Content	1 L
Temperature resistance (hardened)	-25°C to +80°C
Usage	± 0,7 kg/m² / ± 0,5 ltr/m²





Art.-No.: 6.5210.1000

5210

Storage and Transportation

The product may not be stored under +10°C and above +30°C.

The packaging must be protected from direct sunlight and heat.

Cool and moisture free stored the product is tenable for a minimum 2 years in the unopened original packaging.