



Art.-No.: 6.8060.1000

8060

Cutting Compound-S

Characteristics

Highly effective compound on aluminium oxide basis for the polishing of aged as well as for the treatment of fresh clearcoats suitably.

Removes quickly use traces and overspray. Designed to eliminate grain 1500 sanding scratches.

Tech Tip

- No dust formation
- Residues can be cleaned up easily after polishing
- Silicone free and safe for all paint shop applications

Application

Do not use on hot surfaces.

Check for suitability and compatibility before use.

- Shake the polish well before use.
- Apply a small amount of polish on to the surface.
- Place the polishing machine (1500 - 2000 RPM) with light pressure on the surface to be processed and start.
- Apply light pressure to the surface, add a little polish if necessary.
- Repeat the process if necessary.
- Remove the polish residue and splashes with a microfiber cloth.
- It is recommended to treat the surface with high-gloss polish 8070 or anti-hologram polish 8075 to achieve even more of a depth and shine.
- If necessary, clean the surface with 6260 to better remove polish residues and to make any remaining scoring marks visible.



Perfect result in combination with:

Polishing machine 8600 or 8650

Polishing sponge UHS gray 8715 - very hard special sponge for polishing scratch-resistant, due to dried and weathered surfaces

Polishing sponge Violet 8712 - medium hard sponge for polishing well dried paintwork

Microfiber cloth 6255

Cleaning and protective spray 6260



Art.-No.: 6.8060.1000

8060

Technical Data

Colour	white
Viscosity	5 -15 Pas
Density	1,5 kg/l

Storage and Transportation

At storage temperatures of preferably 15 to 20°C original packings may be stored for 24 months. Keep from freezing!